

**Supplemental Specification
2017 Standard Specification Book**

SECTION 05829M

POURABLE JOINT SEAL

Delete Article 1.3 and replace with the following:

1.3 REFERENCES

- A. ASTM C 639: Rheological (Flow) Properties of Elastomeric Sealants
- B. ASTM C 661: Indentation Hardness of Elastomeric – Type Sealants by Means of a Durometer
- C. ASTM C 679: Tack-Free Time of Elastomeric Sealants
- D. ASTM C 719: Adhesion and Cohesion of Elastomeric Joint Sealants Under Cyclic Movement (Hockman Cycle)
- E. ASTM D 412: Vulcanized Rubber and Thermoplastic Elastomers – Tension
- F. ASTM D 4285: Indicating Oil or Water in Compressed Air
- G. ASTM D 5249: Backer Material for Use with Cold- and Hot-Applied Joint Sealants in Portland-Cement Concrete and Asphalt Joints

Delete paragraph 2.1 A3 and replace with the following:

- 3. Applicable for use on highways or bridges.

Delete paragraph 2.1 A4 and Table 1 and replace with the following:

4. Meet the properties listed in Table 1.

Table 1

Property	Requirements	Test Method
Leveling	Self Levels	ASTM C 639
Tack Free Time	150 minutes max.	ASTM C 679
Movement Capability	+100% -50%	ASTM C 719
Ultimate Elongation	1000% min.	ASTM D 412
Hardness	10 - 45 (Shore A) 50 - 80 (Shore OO)	ASTM C 661