

**Supplemental Specification
2017 Standard Specification Book**

SECTION 03056M

SELF-CONSOLIDATING CONCRETE (SCC)

Delete Paragraph 1.3 I through M and replace with the following:

- I. ASTM C 1712: Rapid Assessment of Static Segregation Resistance of Self-Consolidating Concrete Using Penetration Test
- J. American Concrete Institute (ACI) Standards
- K. UDOT Materials Manual of Instruction
- L. UDOT Minimum Sampling and Testing Requirements
- M. UDOT Quality Management Plans

Delete Paragraph 2.1 B through C and replace with the following:

- B. Slump Flow – 20 to 30 inches. Refer to AASHTO T 347.
- C. Rapid Assessment of Static Segregation less than or equal to 15 mm. Refer to ASTM C 1712.